

**COSMOB**

LABORATORIO TECNOLOGICO QUALITÀ



LAB N° 0240

Test Report

n° TR 009319-09.1

Date of receipt:	21/02/2019	For the attention of FARAM 1957 S.p.A. Via Schiavonesca 71, 31040 Giavera del Montello (TV)	
Start of the test:	08/03/2019		
End of the test:	08/03/2019		
Sample identification:	Bianco 68R identified with code 009319-09-01		
Standard:	UNI EN 13721:2004	Title:	Furniture. Assessment of the surface reflectance.

CONDITIONING

Conditioning start date:	21/02/2019
Conditioning end date:	08/03/2019

TEST RESULTS

Type of instrument	Sphere spectrophotometer	
Geometry used	Diffused / 8° (d/8)	
Brightening	D65	
Observer	10°	
Specular measurement with reflection	Included	
Finishing colour	top matt	
Application point Y₁	Application point Y₂	Application point Y₃
84,38	84,37	84,38
Application point Y₄	Application point Y₅	Application point Y₆
84,43	84,42	84,45
Application point Y₇	Application point Y₈	Application point Y₉
84,42	84,43	84,42
Average value Y_m		
84,41		

After the test, the sample is not in compliance with UNI 11191:2006 standard.

Note: Sampling was performed by the customer. The name and the description of the sample are declared by the customer.

END OF THE TEST REPORT N°009319-09.1

This document is the English translation of the report n° RP 009319-09.1

Chemical Area Manager
Dr. Alessandra Cecchini

Laboratory Technical Manager
Eng. Francesco Balducci

Montelabbate: March 28th, 2019.

Digital document digitally signed in accordance with Legislative Decree 82/2005 s.m.i. and related rules, which replaces the paper document and the handwritten signature.

I risultati contenuti nel presente rapporto si riferiscono solamente al campione esaminato. La denominazione del campione è quella indicata dalla ditta richiedente. Il richiedente ha l'obbligo di riprodurre il rapporto di prova per intero. Aggiunte, cancellazioni o alterazioni non sono ammesse.